

SUF-FIX D3 WHITE WOOD GLUE

1 – DESCRIPTION

Suf-Fix D3 White Wood Glue is a formulated cross-linking synthetic emulsion. Its fast setting and water resistance are suitable for rapid production and bond security even under damp conditions.

2 – PROPERTIES

- Fast curing.
- Low press time.
- Extremely high bond strength on numerous substrates.
- Conforms to D3 according to DIN EN 204.
- Very good resistance to chemicals.
- Excellent resistance to moisture and weather conditions.
- Non-shrinking.
- Low odour.

3 - APPLICATIONS

- D3 Adhesive can be used in lamination of HPL to wood based substrates and wood to wood when a good water resistance is required.
- D3 is vinyl acetate homopolymer dispersion with reactive groups with an acidic pH range.
- It is used to adhere all kinds of wooden pieces to each other and used to adhere all kinds of laminate and plates to wooden pieces. Because of the water resistant, it is used in windows having resistance to vapor and moisture, woodworks, doors, external door frames, production of stairs and wooden furniture, high frequency adhering applications, delicacy processes, surface covering of DKS Plates, mounting processes, to adhere decorative papers to surfaces and hard-soft fiber boards to each other.
- D3 exhibits a rapid increase of bond strength when being pressed at temperatures of approx. 20 ° C as well as at higher levels of temperature between 50 and 100 °C. Particularly on hot presses (60-80 ° C) the accelerated increase of bond strength makes D3 most suitable for the lamination of panels with for mica finishing and for post-forming finishing of panel edges and profiles. The resulting water proof bonds exhibit an outstanding heat resistance.
- Dry films of D3 only absorb a very low amount of water. Even after prolonged water immersion the films show no age ability re-emulsify, exhibiting therefore a good water-proof performance of the dried bond.

4 - INSTRUCTIONS

D3 Adhesive can be applied using mechanical glue spreader, brush or hand roller and air activate glue gun.

5- PACKAGING

Product	Weight	Package
D3 White Wood Glue	500 gr	12
D3 White Wood Glue	1 Kg	12
D3 White Wood Glue	3 Kg	4
D3 White Wood Glue	10 Kg	1
D3 White Wood Glue	30 Kg	1

6- STORAGE AND SHELF LIFE

The emulsion must be stored between 5-25°C for a maximum of 12 months from production date.

7- RESTRICTIONS

- Full water resistance is achieved after 7 days. The product should be thoroughly mixed before use.
- Addition of water to D3 Adhesive is not recommended.
- Rotate stock using oldest material first. Do not mix with other adhesives. Protect from freezing.

8- TECHNICAL PROPERTIES

Basis	: Vinyl Acetate polymer
Appearance	: White paste
Density	: 1.05 g/mL
Solids %	: 54±1
Filming Time	: Min. 10 minutes (20°C)
Viscosity	: 14400±800 cps cps at 20°C (Spindle No 6, 20 rpm)
Moisture content in wood	: 8 - 12 %, Increase press time for higher moisture content.
pH	: 5-6
Glue line pressure for hard wood	: 9 - 12 kg/cm ²
Water resistant	: Good (D3-DIN EN204)
Consumption	: 70-130gr/m ²

Material	Press Heat		
	+20 °C	+50 °C	+80 °C
Wood to wood	30 min.	8 min.	4 min.
Coating to wood	20 min.	4 min.	2 min.
Synthetic wood coatings	30 min.	6 min.	3 min.